

HTC 25/25-80

Carbon Grid Reinforcement

Lightweight | Medium Grid | Service temperature up to 80 °C | Corrosion-free

Overview

Bidirectional carbon fiber grid made of 24K rovings (wrapped). Designed for textile-reinforced concrete (TRC) applications requiring efficient crack control and thin-section reinforcement. Suitable for façade panels, thin overlays, precast components, and lightweight structural elements exposed to elevated service temperatures.



Technical Data

Property	Value	Unit	Test method
Material (lengthwise)	Carbon 24K -wrapped	-	-
Material (crosswise)	24K	-	-
Density of carbon fiber	1.78	g/cm ³	-
Binding thread	PES 167 dtex	-	-
Weight (uncoated / coated) approx.	118 / 140	g/m ²	-
Threads per meter (L / C)	34 / 35	threads/m	-
Cross-sectional area (L / C)	31.0 / 31.5	mm ² /m	-
Grid opening	27 × 27	mm	-
Tensile strength (L / C)	75 / 88	kN/m	DIN EN ISO 3341
Tensile strength (fiber) (L / C)	2712 / 3190	N/mm ²	DIN EN ISO 3341
Strain at break (L / C)	1.47 / 1.34	%	DIN EN ISO 3341
Impregnation / Coating	Acrylate	-	-
Max. service temperature	80	°C	-
Roll width	300	cm	-
Roll length	Custom	-	-

DISCLAIMER: Technical data is based on current product specifications. Users are responsible for verifying suitability for the intended application. Product specifications may change without notice. Current Terms and Conditions apply.